



X_Butyl® BROMOBUTYL & CHLOROBUTYL RUBBER

Halobutyl rubber is produced in a continuous process through reaction of regular butyl rubber with bromine or chlorine to form bromobutyl or chlorobutyl, respectively. Halogenation allows co-vulcanization and improved compatibility with other diene rubber types, in addition to improvements in the vulcanization rates, states of cure and reversion resistance. Many of the properties of halobutyl vulcanizates are virtually identical, regardless of the halogen employed. With bromobutyl rubber however, the brominated sites are more reactive,

resulting in faster cure and better adhesion to unsaturated rubber types. When the compounds based on either brominated or chlorinated X_Butyl® are correctly formulated and processed, the end-products have:

- very low permeability to gases and liquids
- excellent resistance to weathering, ozone and heat
- good resistance to acidic and basic chemicals
- high hysteresis for energy absorption
- good low-temperature flexibility

PRODUCT PORTFOLIO

		Mooney [MU]	Halogen [wt%]	Ash [wt%]	Volatiles [wt%]
Bromobutyl Rubber	X_Butyl® BB 2030	32	1.8	<0.7	<0.7
	X_Butyl® BB 2040	39	1.8	<0.7	<0.7
	X_Butyl® BB X2	46	1.8	<0.7	<0.7
Chlorobutyl Rubber	X_Butyl® CB 1240	38	1.25	<0.5	<0.5

APPLICATIONS

The versatility of halobutyl rubber has led to its use in a diverse range of tire and non-tire applications including:

- tire innerliner
- pharmaceutical stoppers
- hoses
- protective clothing
- tank linings
- high traction footwear
- adhesives



TIRE AND SPECIALTY RUBBERS GLOBAL FOOTPRINT



WE ARE HAPPY TO SUPPORT YOUR BUSINESS

NAFTA

Technical Service

Judy Douglas

E-mail: judy.douglas@arlanxeo.com

Phone: +1 412 809 3547

Sales

John Sawaya

E-mail: john.sawaya@arlanxeo.com

Phone: +1 412 809 1530

EMEA

Technical Service

Luc ter Bogt

E-mail: luc.terbogt@arlanxeo.com

Phone: +49 221 8885 3998

Sales

Marco Eira

E-mail: marco.eira@arlanxeo.com

Phone: +41 26 422 8354

APAC

Technical Service

Esther Han

E-mail: esther.han@arlanxeo.com

Phone: +65 6725 5709

Sales

JooSang Kim

E-mail: joosang.kim@arlanxeo.com

Phone: +65 6725 5872

LATAM

Technical Service

Marcus Moutinho

E-mail: marcus.moutinho@arlanxeo.com

Phone: +55 21 2677 1219

Sales

Sergio Botafogo

E-mail: sergio.botafogo@arlanxeo.com

Phone: +55 21 2677 1344

Please contact us for additional information or visit us at
www.tsr.arlanxeo.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

Health and Safety Information: Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling the ARLANXEO products mentioned in this publication. For materials mentioned which are not ARLANXEO products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be followed. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., *safety data sheets and product labels*. Consult your ARLANXEO representative or contact the Product Safety and Regulatory Affairs Department.

X_Butyl® is a registered trademark of ARLANXEO Switzerland S.A.

Note: The information contained in this publication is current as of May 2017.

Please contact ARLANXEO USA LLC to determine if this publication has been revised.