

X_BUTYL[®] CHLOROBUTYL RUBBER FOR CURING ENVELOPES

Curing envelopes are a key component in the retreading of tires. During this process the tire composed of uncured cushion gum and a pre-cured tread is encased in a flexible rubber envelope which conforms to the shape of the tire. A ring is then applied to the inside of the tire creating a tight seal. The tire is then placed in a curing chamber which applies heat and pressure to cure the unvulcanized cushion gum bonding the pre-cured tread to the tire casing. As these envelopes undergo numerous cycles, the choice of polymer is very important. While the use of regular X_Butyl[®] provides long lasting envelopes, chlorinated X_Butyl[®] may also be used in order to improve the production throughput of the curing envelopes. While these envelopes may have shorter lifetimes as those based on regular butyl rubber, compared to other polymers they possess:

- very low permeability to gases and steam
- resistance to heat
- good hot tear and crack growth resistance
- low compression and permanent set

PRODUCT PROPERTIES

| Grade | X_Butyl [®] CB 1240 | | |
|--|------------------------------|--|--|
| Mooney Viscosity (ML (1+ 8) @ 125°C, MU) | 38 | | |
| Halogen (wt%) | 1.25 | | |
| Volatiles (wt%) | <0.5 | | |

TYPICAL COMPOUND FORMULATION

| Ingredient | phr | Mechanical Properties | Unit | Typical Value* |
|------------------------------|-----|---------------------------------|-----------|----------------|
| X_Butyl [®] CB 1240 | 100 | Hardness | (ShA) | 48 |
| Carbon Black | 50 | Tensile Strength | (MPa) | 13.0 |
| Stearic Acid | 1 | Modulus 100% | (MPa) | 1.2 |
| Process Aid | 4 | Modulus 200% | (MPa) | 2.3 |
| Oil | 15 | Elongation at break | (%) | 755 |
| | 3 | Tear Strength | (kN/m) | 36 |
| Amylphenol disulfide | | Crack Growth Resistance to 600% | (kcycles) | >250 |
| | 4 | Permanent Set | (%) | 4 |

*These items are provided as general information only. They are approximate values and are not considered part of the product specifications. Please contact your regional representative for additional information.

TIRE AND SPECIALTY RUBBERS GLOBAL FOOTPRINT



WE ARE HAPPY TO SUPPORT YOUR BUSINESS

NORAM

Technical Service Sharon Guo E-mail: sharon.guo@arlanxeo.com Phone: +1 519 953 1728

Sales

Jay Capelli E-mail: jay.capelli@arlanxeo.com Phone: +1 412 809 2237

EMEA

Technical Service Wilfried Braubach E-mail: wilfried.braubach@arlanxeo.com Phone: +49 221 8885 1085

Sales

Marco Eira E-mail: marco.eira@arlanxeo.com Phone: +41 26 422 8354

APAC

Technical Service Esther Han E-mail: esther.han@arlanxeo.com Phone: +65 6725 5709

Sales JooSang Kim E-mail: joosang.kim@arlanxeo.com Phone: +65 6725 5872

LATAM

Technical Service Marcus Moutinho E-mail: marcus.moutinho@arlanxeo.com Phone: +55 21 2677 1219

Sales Sergio Botafogo E-mail: sergio.botafogo@arlanxeo.com Phone: +55 21 2677 1344

Please contact us for additional information or visit us at www.tsr.arlanxeo.com

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

Health and Safety Information: Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling the ARLANXEO products, mentioned in this publication. For materials mentioned which are not ARLANXEO products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be followed. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., safety data sheets and product labels. Consult your ARLANXEO representative or contact the Product Safety and Regulatory Affairs Department.



X_Butyl[®] is a registered trademark of ARLANXEO Switzerland S.A. Note: The information contained in this publication is current as of September 2018. Please contact ARLANXEO USA LLC to determine if this publication has been revised.